

SHUMAN COMPOUND: DATA SHEET

DESCRIPTION: PPO FLAME RETARDANT, 211 BLACK, CUSTOM COLORS

OFFERS THIS COMBINATION OF PROPERTIES:

EXCELLENT FLAME RETARDANCY, EASY PROCESSABILITY, GOOD IMPACT STRENGTH, GOOD CHEMICAL RESISTANCE, SELF EXTINGUISHING, UL

TYPICAL PROPERTIES

MECHANICAL PROPERTIES

	<u>VALUE</u>	<u>UNITS</u>	<u>TEST METHODS</u>
IZOD IMPACT STRENGTH (NOTCHED, 1/8" THICK SPECIMEN)	3.0	FT-LBS/IN	ASTM D-256
TENSILE STRENGTH	6800	PSI	ASTM D-638
ROCKWELL HARDNESS	116	R	ASTM D-785

THERMAL PROPERTIES

HEAT DEFLECTION TEMPERATURE @ 264 PSI	195	°F	ASTM D-648
VICAT SOFTENING TEMPERATURE	260	°F	ASTM D-1525

FLAME-RETARDANT PROPERTIES

FLAME CLASS RATING 0.125 " (3.18mm) THICK SPECIMEN	5VA		UL 94 *not listed
FLAME CLASS RATING 0.062" (1.57mm) THICK SPECIMEN	V0		UL 94 *not listed

OTHER PROPERTIES

SPECIFIC GRAVITY	1.1		ASTM D-792
MELT FLOW RATE	1.5	GM/10 MIN.	ASTM D-1238

SUGGESTED DRYING CONDITIONS:

	<u>TEMPERATURE °F</u>		<u>TIME (HOURS)</u>	
	<u>MIN.</u>	<u>MAX.</u>	<u>MIN.</u>	<u>MAX.</u>
DEHUMIDIFYING DRYER	180	220	2	4
TRAY DRYER NOTE: DEPTH OF GRANULES IN TRAY DRYER SHOULD NOT EXCEED 1½ IN. (38.1mm)	180	220	2	4

SUGGESTED PROCESSING CONDITIONS:

EXTRUSION: 380° - 430°

INJECTION: 430° - 500°

"DISCLAIMER: The information in this Material Safety Data Sheet is believed to be correct as of the date issued. NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE IS MADE. User is responsible for determining whether the product is fit for a particular purpose and suitable for user's method of use or application. Given the variety of factors that can affect the use and application of a product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the product to determine whether it is fit for a particular purpose and suitable for user's method of use or application. No suggestions for use are intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patents or to violate any Federal, State or local laws."