

TECHNICAL DATA SHEET

Shuman Compound:

ABS Flame Retardant SP790 Black and Custom Colors

Offers this combination of properties:

UL recognized, Excellent flame retardancy, Good impact strength, Good chemical resistance, Self-extinguishing

TYPICAL PROPERTIES

<u>MECHANICAL PROPERTIES</u>	<u>VALUE</u>	<u>UNITS</u>	<u>TEST METHODS</u>
Izod Impact Strength (Notched, 1/8" Thick Specimen)	4.0 (+/- 0.5)	FT-LBS/IN	ASTM D-256
Rockwell Hardness	105	R	ASTM D-785
Tensile Strength at Yield	6500	PSI	ASTM D-638
<u>THERMAL PROPERTIES</u>			
Coefficient of Linear Thermal Expansion	9.3 x 10 ⁻⁵ in/in	deg. C	ASTM D-696
Hot Wire Ignition (HWI) 0.101" Thick Specimen	33.4	SEC. TO IGNITE	UL 746A
High Current Arc Ignition (HAI) 0.100" Thick Specimen	199.4	ARCS	UL 746A
High Voltage Arc Tracking (HVTR) 0.100" Thick Specimen	5.873	IN./MIN	UL 746A
Comparative Track Index (CTI) 0.100" Thick Specimen	250	VOLTS	UL 746A
<u>FLAME RETARDANT PROPERTIES</u>			
Flame Class Rating 0.100" (2.54 mm) Thick Specimen	V0		UL 94
<u>OTHER PROPERTIES</u>			
Specific Gravity	1.2		ASTM D-792
Melt Flow Rate	4 (+/-2)	GM/10 MIN.	ASTM D-1238

SUGGESTED PROCESSING CONDITIONS

<u>DRYING CONDITIONS:</u>	<u>TEMPERATURE (deg. F)</u>		<u>TIME (HOURS)</u>	
	<u>MIN.</u>	<u>MAX.</u>	<u>MIN.</u>	<u>MAX.</u>
Dehumidifying Dryer	190	200	2	24
Tray Dryer NOTE: Depth of granules in tray dryer should not exceed 1½ in. (38.1 mm)	170	200	4	24

TEMPERATURE CONDITIONS:

INJECTION: 400 - 440F
EXTRUSION: 350 - 420F

NOTICE: THE INFORMATION CONTAINED HEREIN IS BASED ON WHAT WE BELIEVE TO BE RELIABLE DATA, BUT SHUMAN PLASTICS, INC. MAKES NO WARRANTIES EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. BECAUSE SHUMAN HAS NO CONTROL OVER THE USE TO WHICH OTHERS MAY PUT THE PRODUCT, IT DOES NOT SUGGEST OR REPRESENT THAT THE SAME RESULTS AS THOSE REFERRED TO HEREIN WILL BE OBTAINED BY ANOTHER USER. EACH USER OF THE PRODUCT AND THE COMPOSITIONS MENTIONED HEREIN SHOULD MAKE HIS OWN TESTS PRIOR TO PURCHASE TO DETERMINE THE PRODUCT'S SUITABILITY FOR HIS OWN PARTICULAR USES.

NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A RECOMMENDATION FOR THE USE IN VIOLATION OF ANY EXISTING PATENT, FOREIGN OR DOMESTIC, OR OF APPLICABLE LAWS AND REGULATIONS.

DATA SHOWN ARE THE AVERAGE RESULTS OF OUR OWN TESTS AND SHOULD NOT BE USED FOR SPECIFICATIONS

DOC REV 11/17