

## TECHNICAL DATA SHEET

### Shuman Compound:

Polypropylene Copolymer 502C Utility Black

#### Offers this combination of properties:

Good impact strength, Excellent chemical resistance, Excellent processability

---

### TYPICAL PROPERTIES

---

#### MECHANICAL PROPERTIES

Izod Impact Strength (Notched, 1/8" Thick Specimen)  
Tensile Strength

#### VALUE

1.8 min.  
4057

#### UNITS

FT-LBS/IN  
PSI

#### TEST METHODS

ASTM D-256  
ASTM D-638

#### THERMAL PROPERTIES

Heat Deflection Temperature @ 264 PSI  
Vicat Softening Temperature

117  
300

deg. F  
deg. F

ASTM D-648  
ASTM D-1525

#### OTHER PROPERTIES

Specific Gravity  
Melt Flow Rate

.9  
5 (+/-2)  
10 (+/-2)  
15 (+/-2)  
20 (+/-2)

GM/10 MIN.  
GM/10 MIN.  
GM/10 MIN.  
GM/10 MIN.

ASTM D-792  
ASTM D-1238

---

### SUGGESTED PROCESSING CONDITIONS

---

#### TEMPERATURE CONDITIONS:

370-420F

NOTICE: THE INFORMATION CONTAINED HEREIN IS BASED ON WHAT WE BELIEVE TO BE RELIABLE DATA, BUT SHUMAN PLASTICS, INC. MAKES NO WARRANTIES EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. BECAUSE SHUMAN HAS NO CONTROL OVER THE USE TO WHICH OTHERS MAY PUT THE PRODUCT, IT DOES NOT SUGGEST OR REPRESENT THAT THE SAME RESULTS AS THOSE REFERRED TO HEREIN WILL BE OBTAINED BY ANOTHER USER. EACH USER OF THE PRODUCT AND THE COMPOSITIONS MENTIONED HEREIN SHOULD MAKE HIS OWN TESTS PRIOR TO PURCHASE TO DETERMINE THE PRODUCT'S SUITABILITY FOR HIS OWN PARTICULAR USES.

NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A RECOMMENDATION FOR THE USE IN VIOLATION OF ANY EXISTING PATENT, FOREIGN OR DOMESTIC, OR OF APPLICABLE LAWS AND REGULATIONS.

DATA SHOWN ARE THE AVERAGE RESULTS OF OUR OWN TESTS AND SHOULD NOT BE USED FOR SPECIFICATIONS

DOC REV 11/17