

TECHNICAL DATA SHEET

Shuman Compound:

PC/ABS Alloy Flame Retardant FR310 Utility Black, FR380 Grey (formerly FR705)

Offers this combination of properties:

Excellent flame retardancy, Good impact strength, Easy processability, Good chemical resistance

TYPICAL PROPERTIES

MECHANICAL PROPERTIES

	<u>VALUE</u>	<u>UNITS</u>	<u>TEST METHODS</u>
Izod Impact Strength (Notched, 1/8" Thick Specimen)	9 (+/-1.5)	FT-LBS/IN	ASTM D-256
Flex Modulus	350,000 (+/-30,000)	PSI	ASTM D-790
Tensile Strength	7000 (+/-1000)	PSI	ASTM D-638

FLAME RETARDANT PROPERTIES

Flame Class Rating 0.125" (3.22 mm) Thick Specimen	V0		UL 94 *not listed
--	----	--	-------------------

OTHER PROPERTIES

Specific Gravity	1.13		ASTM D-792
Melt Flow Rate	5 (+/-3)	GM/10 MIN.	ASTM D-1238

SUGGESTED PROCESSING CONDITIONS

DRYING CONDITIONS:

	<u>TEMPERATURE (deg. F)</u>		<u>TIME (HOURS)</u>	
	<u>MIN.</u>	<u>MAX.</u>	<u>MIN.</u>	<u>MAX.</u>
Dehumidifying Dryer	175	230	3	4

TEMPERATURE CONDITIONS:

460-530F

NOTICE: THE INFORMATION CONTAINED HEREIN IS BASED ON WHAT WE BELIEVE TO BE RELIABLE DATA, BUT SHUMAN PLASTICS, INC. MAKES NO WARRANTIES EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. BECAUSE SHUMAN HAS NO CONTROL OVER THE USE TO WHICH OTHERS MAY PUT THE PRODUCT, IT DOES NOT SUGGEST OR REPRESENT THAT THE SAME RESULTS AS THOSE REFERRED TO HEREIN WILL BE OBTAINED BY ANOTHER USER. EACH USER OF THE PRODUCT AND THE COMPOSITIONS MENTIONED HEREIN SHOULD MAKE HIS OWN TESTS PRIOR TO PURCHASE TO DETERMINE THE PRODUCT'S SUITABILITY FOR HIS OWN PARTICULAR USES.

NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A RECOMMENDATION FOR THE USE IN VIOLATION OF ANY EXISTING PATENT, FOREIGN OR DOMESTIC, OR OF APPLICABLE LAWS AND REGULATIONS.

DATA SHOWN ARE THE AVERAGE RESULTS OF OUR OWN TESTS AND SHOULD NOT BE USED FOR SPECIFICATIONS

DOC REV 11/17