

TECHNICAL DATA SHEET

Shuman Compound:

Polycarbonate Flame Retardant FR910V0 Utility Black, FR980V0 Grey

Offers this combination of properties:

Good impact strength, Easy processability, Self-extinguishing

TYPICAL PROPERTIES

<u>MECHANICAL PROPERTIES</u>	<u>VALUE</u>	<u>UNITS</u>	<u>TEST METHODS</u>
Izod Impact Strength (Notched, 1/8" Thick Specimen)	12	FT-LBS/IN	ASTM D-256
Rockwell Hardness	70	M	ASTM D-785
Tensile Strength	9500	PSI	ASTM D-638
<u>THERMAL PROPERTIES</u>			
Heat Deflection Temperature @ 264 PSI	262	deg. F	ASTM D-648
Vicat Softening Temperature	310	deg. F	ASTM D-1525
<u>FLAME RETARDANT PROPERTIES</u>			
Flame Class Rating 0.062" (1.57 mm) Thick Specimen	V-0/5VA		UL 94 *not listed
<u>OTHER PROPERTIES</u>			
Specific Gravity	1.2		ASTM D-792
Melt Flow Rate	10 (+/-2)	GM/10 MIN.	ASTM D-1238
	15 (+/-2)	GM/10 MIN.	
	20 (+/-2)	GM/10 MIN.	

SUGGESTED PROCESSING CONDITIONS

<u>DRYING CONDITIONS:</u>	<u>TEMPERATURE (deg. F)</u>		<u>TIME (HOURS)</u>	
	<u>MIN.</u>	<u>MAX.</u>	<u>MIN.</u>	<u>MAX.</u>
Dehumidifying Dryer	250	260	2-3	24
Tray Dryer NOTE: Depth of granules in tray dryer should not exceed 1 in. (25.4 mm)	250	260	4-6	24

TEMPERATURE CONDITIONS:

510-550F

NOTICE: THE INFORMATION CONTAINED HEREIN IS BASED ON WHAT WE BELIEVE TO BE RELIABLE DATA, BUT SHUMAN PLASTICS, INC. MAKES NO WARRANTIES EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. BECAUSE SHUMAN HAS NO CONTROL OVER THE USE TO WHICH OTHERS MAY PUT THE PRODUCT, IT DOES NOT SUGGEST OR REPRESENT THAT THE SAME RESULTS AS THOSE REFERRED TO HEREIN WILL BE OBTAINED BY ANOTHER USER. EACH USER OF THE PRODUCT AND THE COMPOSITIONS MENTIONED HEREIN SHOULD MAKE HIS OWN TESTS PRIOR TO PURCHASE TO DETERMINE THE PRODUCT'S SUITABILITY FOR HIS OWN PARTICULAR USES.

NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A RECOMMENDATION FOR THE USE IN VIOLATION OF ANY EXISTING PATENT, FOREIGN OR DOMESTIC, OR OF APPLICABLE LAWS AND REGULATIONS.

DATA SHOWN ARE THE AVERAGE RESULTS OF OUR OWN TESTS AND SHOULD NOT BE USED FOR SPECIFICATIONS

DOC REV 11/17