

TECHNICAL DATA SHEET

Shuman Compound:

Polypropylene Homopolymer 510 Utility Black

Offers this combination of properties:

Excellent chemical resistance, Excellent processability

TYPICAL PROPERTIES

MECHANICAL PROPERTIES Izod Impact Strength (Notched, 1/8" Thick Specimen) Tensile Strength	<u>VALUE</u>	UNITS	TEST METHODS
	.6-1.0	FT-LBS/IN	ASTM D-256
	4472	PSI	ASTM D-638
THERMAL PROPERTIES Heat Deflection Temperature @ 264 PSI Vicat Softening Temperature	122	deg. F	ASTM D-648
	299	deg. F	ASTM D-1525
OTHER PROPERTIES Specific Gravity Melt Flow Rate	.9 5 (+/-2) 10 (+/-2) 15 (+/-2) 20 (+/-2)	GM/10 MIN. GM/10 MIN. GM/10 MIN. GM/10 MIN.	ASTM D-792 ASTM D-1238

SUGGESTED PROCESSING CONDITIONS

TEMPERATURE CONDITIONS:

370-420F

NOTICE: THE INFORMATION CONTAINED HEREIN IS BASED ON WHAT WE BELIEVE TO BE RELIABLE DATA, BUT SHUMAN PLASTICS, INC. MAKES NO WARRANTIES EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. BECAUSE SHUMAN HAS NO CONTROL OVER THE USE TO WHICH OTHERS MAY PUT THE PRODUCT, IT DOES NOT SUGGEST OR REPRESSENT THAT THE SAME RESULTS AS THOSE REFERRED TO HEREIN WILL BE OBTAINED BY ANOTHER USER. EACH USER OF THE PRODUCT AND THE COMPOSITIONS MENTIONED HEREIN SHOULD MAKE HIS OWN TESTS PRIOR TO PURCHASE TO DETERMINE THE PRODUCT'S SUITABILITY FOR HIS OWN PARTICULAR USES.

NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A RECOMMENDATION FOR THE USE IN VIOLATION OF ANY EXISTING PATENT, FOREIGN OR DOMESTIC, OR OF APPLICABLE LAWS AND REGULATIONS.

DATA SHOWN ARE THE AVERAGE RESULTS OF OUR OWN TESTS AND SHOULD NOT BE USED FOR SPECIFICATIONS

DOC REV 11/17