

## TECHNICAL DATA SHEET

### Shuman Compound:

Polystyrene Medium Impact 811 Utility Black, 881 Grey

### Offers this combination of properties:

Easy processability, Good gloss, Good surface appearance

---

## TYPICAL PROPERTIES

---

### MECHANICAL PROPERTIES

	<u>VALUE</u>	<u>UNITS</u>	<u>TEST METHODS</u>
Izod Impact Strength (Notched, 1/8" Thick Specimen)	0.9-1.3	FT-LBS/IN	ASTM D-256
Rockwell Hardness	60	L	ASTM D-785
Tensile Strength	5200	PSI	ASTM D-638

### THERMAL PROPERTIES

Heat Deflection Temperature @ 264 PSI	190	deg. F	ASTM D-648
Vicat Softening Temperature	210	deg. F	ASTM D-1525

### OTHER PROPERTIES

Specific Gravity	1.05		ASTM D-792
Melt Flow Rate	6 (+/-2) 8 (+/-2) 10 (+/-2)	GM/10 MIN.	ASTM D-1238

---

## SUGGESTED PROCESSING CONDITIONS

---

### TEMPERATURE CONDITIONS:

400 - 440F

NOTICE: THE INFORMATION CONTAINED HEREIN IS BASED ON WHAT WE BELIEVE TO BE RELIABLE DATA, BUT SHUMAN PLASTICS, INC. MAKES NO WARRANTIES EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. BECAUSE SHUMAN HAS NO CONTROL OVER THE USE TO WHICH OTHERS MAY PUT THE PRODUCT, IT DOES NOT SUGGEST OR REPRESENT THAT THE SAME RESULTS AS THOSE REFERRED TO HEREIN WILL BE OBTAINED BY ANOTHER USER. EACH USER OF THE PRODUCT AND THE COMPOSITIONS MENTIONED HEREIN SHOULD MAKE HIS OWN TESTS PRIOR TO PURCHASE TO DETERMINE THE PRODUCT'S SUITABILITY FOR HIS OWN PARTICULAR USES.

NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A RECOMMENDATION FOR THE USE IN VIOLATION OF ANY EXISTING PATENT, FOREIGN OR DOMESTIC, OR OF APPLICABLE LAWS AND REGULATIONS.

DATA SHOWN ARE THE AVERAGE RESULTS OF OUR OWN TESTS AND SHOULD NOT BE USED FOR SPECIFICATIONS

DOC REV 11/17